



Antioxidants and
light stabilizers

Product range
selection guide

Phenolic
Antioxidants

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 1010																
SONGNOX® 1076																
SONGNOX® 1135																
SONGNOX® 2450																
SONGNOX® 3114																
SONGNOX® 1035																
SONGNOX® 1098																
SONGNOX® 1330																
SONGNOX® 5650																
SONGNOX® 1024																

Aminic
Antioxidants

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 5057																
SONGNOX® 5067																

Phosphite
Antioxidants

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 1680																
SONGNOX® 6260																
SONGNOX® 6280																
SONGNOX® PQ																
SONGNOX® 9228																
SONGNOX® 9228T																

Thioester
Antioxidants

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® DSTDP																
SONGNOX® DLTDP																
SONGNOX® DMTDP																
SONGNOX® DTDTP																

Recommended Suitable

Hindered
Amine Light
Stabilizers
(HALS)

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGSORB® 2920																
SONGSORB® 7700																
SONGSORB® 3853																
SONGSORB® 9440																
SONGSORB® 6220																
SONGSORB® 7830																
SONGSORB® 2020																
SONGSORB® 1190																

UV
Absorbers
(UVAs)

		ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGSORB® 1000																
SONGSORB® 2340																
SONGSORB® 3260																
SONGSORB® 3290																
SONGSORB® 3600																
SONGSORB® 5710																
SONGSORB® 7120																
SONGSORB® 2908																
SONGSORB® 8100																
SONGSORB® 3120																
SONGSORB® 1577																
SONGSORB® 1164																
SONGSORB® B5075																

Phenolic
Antioxidants

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)		TGA (°C, % mass loss)	
SONGNOX® 1010 Tetrakis[methylene-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate] methane CAS NO. 6683-19-8 PW, FF, DF		1178	110.0 ~ 125.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 < 0.1 < 50.0 < 0.1 48.0 24.2 > 50.0	353 370 425 5% 10% 50%	
SONGNOX® 1076 Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate CAS NO. 2082-79-3 CP, SB, LQ		531	50.0 ~ 55.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	0.5 > 50.0 > 50.0 < 0.1 > 50.0 > 50.0 > 50.0	330 347 387 5% 10% 50%	
SONGNOX® 1135 Benzenepropanoic acid, 3,5-bis(1,1-dimethylethyl)-4-hydroxy-, C7-9-branched alkyl esters CAS NO. 125643-61-0 LQ		390	—	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	> 50.0 > 50.0 > 50.0 > 50.0 > 50.0 > 50.0 > 50.0	257 278 328 5% 10% 50%	
SONGNOX® 2450 Triethylene glycol-bis-3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionate CAS NO. 36443-68-2 PW, FF, DW		587	76.0 ~ 80.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 < 0.1 > 50.0 9.0 10.0 0.5 > 50.0	326 345 396 5% 10% 50%	
SONGNOX® 3114 Tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate CAS NO. 27676-62-6 PW, FF		784	218.0 ~ 223.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 < 0.1 45.0 < 0.1 22.0 21.0 45.0	330 344 374 5% 10% 50%	
SONGNOX® 1035 Thiodiethylenebis[3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate] CAS NO. 41484-35-9 PW, FF		643	> 65.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 0.8 > 50.0 1.1 > 50.0 > 50.0 > 50.0	322 339 375 5% 10% 50%	
SONGNOX® 1098 N,N'-hexamethylenebis(3,5-di-tert-butyl-4-hydroxyhydrocinnamamide) CAS NO. 23128-74-7 PW, FF		637	156.0 ~ 162.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 < 0.1 2.5 5.5 < 0.1 < 0.1 0.7	336 350 418 5% 10% 50%	
SONGNOX® 1330 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene CAS NO. 1709-70-2 PW, FF		775	241.0 ~ 247.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 0.9 22.0 < 0.1 30.0 22.0 36.0	368 391 446 5% 10% 50%	

SONGNOX® 5650 2,6-di-tert-butyl-4-(4,6-bis(octylthio)-1,3,5-triazin-2-ylamino) phenol CAS NO. 991-84-4 PW, GR		589	94.0 ~ 96.0	Squalane < 0.05 n-Hexane 6.50 Acetone > 50.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	348 362 401	5% 10% 50%
SONGNOX® 1024 1,2-bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl) hydrazine CAS NO. 32687-78-8 PW, FF, FG		553	221.0 ~ 232.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 5.0 Ethanol 1.0 Toluene < 0.1 Xylene < 0.1 Ethyl acetate 0.6	307 319 359	5% 10% 50%



Aminic
Antioxidants

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)	
SONGNOX® 5057 Mixture of butylated & octylated diphenylamine CAS NO. 68411-46-1 LQ		Mixture of butyl, octyl diphenylamine	—	Squalane > 50 n-Hexane > 50 Acetone > 50 Ethanol > 50 Toluene > 50 Xylene > 50 Ethyl acetate > 50	235 5% 255 10% 320 50%	
SONGNOX® 5067 Bis(nonylphenyl)amine CAS NO. 36878-20-3 LQ		422	—	n-Hexane > 50 Acetone > 50 Ethanol > 50 Toluene > 50 Xylene > 50 Ethyl acetate > 50	266 5% 287 10% 350 50%	






Thioester
Antioxidants



		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)	
SONGNOX® DSTDP Distearyl thiodipropionate CAS NO. 693-36-7 PW, SB		683	63.5 ~ 68.5	Squalane 0.1 n-Hexane 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene 4.6 Xylene 4.1 Ethyl acetate < 0.1	324 5% 348 10% 389 50%	
SONGNOX® DLTDP Dilauryl thiodipropionate CAS NO. 123-28-4 PW, SB, LQ		515	38.0 ~ 41.0	Squalane 2.6 n-Hexane > 50.0 Acetone > 50.0 Ethanol 0.3 Toluene > 50.0 Xylene 46.0 Ethyl acetate 29.0	284 5% 313 10% 361 50%	
SONGNOX® DMTDP Dimyristyl thiodipropionate CAS NO. 16545-54-3 PW, SB		571	49.0 ~ 54.0	Squalane < 0.05 n-Hexane 8.0 Acetone 2.0 Ethanol < 0.1 Toluene 41.0 Xylene 33.0 Ethyl acetate 4.1	296 5% 316 10% 367 50%	
SONGNOX® DTDTP Ditridecyl thiodipropionate CAS NO. 10595-72-9 LQ		543	—	Squalane > 50.0 n-Hexane > 50.0 Acetone > 50.0 Ethanol 5.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	300 5% 331 10% 374 50%	


Phosphite
Antioxidants

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)	
SONGNOX® 1680 Tris(2,4-di-tert-butylphenyl) phosphite CAS NO. 31570-04-4 PW, FF		647	181.0 ~ 187.0	Squalane < 0.05 n-Hexane 10.0 Acetone 1.3 Ethanol < 0.1 Toluene 25.0 Xylene 24.0 Ethyl acetate 5.0	286 5% 305 10% 362 50%	
SONGNOX® 6260 Bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite CAS NO. 26741-53-7 PW, FF		605	170.0 ~ 180.0	Squalane < 0.05 n-Hexane 2.0 Acetone 3.0 Ethanol < 0.1 Toluene 26.0 Xylene 17.0 Ethyl acetate 0.7	306 5% 329 10% 382 50%	
SONGNOX® 6280 SONGNOX® 6260: Mg, Al talcite = 93 : 7 CAS NO. 26741-53-7, 11097-59-9 PW, FF		—	—	—	—	—
SONGNOX® PQ Phosphorous trichloride, reaction products with 1,1'-biphenyl and 2,4-bis (1,1-dimethylethyl) phenol CAS NO. 119345-01-6 PW, SB		1035	75.0 ~ 100.0	Squalane 0.1 n-Hexane > 50.0 Acetone 9.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	296 5% 325 10% 423 50%	
SONGNOX® 9228 Bis (2,4-dicumylphenyl) pentaerythritol diphosphite CAS NO. 154862-43-8 PW, FF		852	>228.0	n-Hexane < 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene 4.0 Xylene 5.0 Ethyl acetate < 0.1	365 5% 384 10% 414 50%	
SONGNOX® 9228T Bis (2,4-dicumylphenyl) pentaerythritol diphosphite plus 1% triisopropanol amine CAS NO. 154862-43-8 PW		852	>228.0	n-Hexane < 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene < 0.1 Xylene < 0.1 Ethyl acetate < 0.1	365 5% 384 10% 414 50%	

Hindered Amine Light Stabilizers (HALS)







		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)	
SONGSORB® 2920 Bis (1,2,2,6,6-pentamethyl-4-piperidinyI)-sebacate and 1-(Methyl)-8-(1,2,2,6,6-pentamethyl-4-piperidinyI)-sebacate CAS NO. 41556-26-7 & 82919-37-7 LQ		509	—	n-Hexane > 50.0 Acetone > 50.0 Ethanol > 50.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	220 242 304	5% 10% 50%
SONGSORB® 7700 Bis(2,2,6,6-tetramethyl-4-piperidinyI) sebacate CAS NO. 52829-07-9 PW, DF		481	81.0 ~ 85.0	n-Hexane < 0.1 Acetone 35.0 Ethanol > 50.0 Toluene > 50.0 Xylene 48.0 Ethyl acetate 38.0	245 261 302	5% 10% 50%
SONGSORB® 3853 2,2,6,6-tetramethylpiperidine-4-yl-hexadecanoate and 2,2,6,6-tetramethylpiperidine-4-yl-octadecanoate CAS NO. 167078-06-0 / 86403-32-9 (EU) SL		—	> 29.0	n-Hexane 0.2 Acetone 9.0 Ethanol 8.0 Toluene 27.0 Xylene 23.0 Ethyl acetate 12.0	233 250 292	5% 10% 50%
SONGSORB® 9440 1,6-hexanediamine, N,N'-bis (2,2,6,6-tetramethyl-4-piperidinyI)-, polymer with 2,4,6-trichloro-1,3,5-triazine, reaction products with 2,4,4-trimethyl-2-pentanamine CAS NO. 70624-18-9 / 71878-19-8 SB		2000 ~3100	(Softening) 100.0 ~ 135.0	n-Hexane 6.0 Acetone > 50.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	407 459	10% 50%
SONGSORB® 6220 Butanedioic acid, 1,4-dimethyl ester, polymer with 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine-ethanol CAS NO. 65447-77-0 SB		3100 ~ 4000	—	n-Hexane < 0.1 Acetone 40.0 Ethanol < 0.1 Toluene 15 Xylene 35.0 Ethyl acetate 21.0	333 360	10% 50%

SONGSORB® 7830 Mixture of SONGSORB® 9440 and SONGSORB® 6220 SB	SONGSORB® 9440 : SONGSORB® 6220 = 1:1	—	—	—	—
SONGSORB® 2020 1,6-hexanediamine, N,N'-bis (2,2,6,6-tetramethyl-4- piperidinyI)-,polymer with 2,4,6-trichloro-1,3,5-triazine, reaction products with N-butyl-1-butanamine and N-butyl-2,2,6,6-tetramethyl- 4-piperidinamine CAS NO.192268-64-7 SB		2600 ~ 3400	120.0 ~ 150.0	n-Hexane Acetone Ethanol > 50.0 > 50.0 > 50.0	431 466 10% 50%
SONGSORB® 1190 1,3,5-triazine-2,4,6-triamine, N2,N2"-1,2-ethanediylbis [N2-[3-[[4,6-bis[butyl (1,2,2,6,6-pentamethyl-4- piperidinyI)amino]-1,3,5- triazin-2-yl]amino]propyl]- N',N"-dibutyl-N',N"-bis (1,2,2,6,6-pentamethyl-4- piperidinyI)- CAS NO. 106990-43-6 SB		2286	115.0 ~ 150.0	n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate < 0.1 0.2 < 0.1 25.0 24.0 0.9	427 457 10% 50%









UV DEFENSE
that drives durability

UV Absorbers (UVAs)

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)	
SONGSORB® 1000 2-(2'-hydroxy-5'-methylphenyl) benzotriazole CAS NO. 2440-22-4 PW		225	128.0 ~ 132.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 3.0 Ethanol < 0.1 Toluene 7.1 Xylene 6.1 Ethyl acetate 5.1	225 242 289	5% 10% 50%
SONGSORB® 2340 2-[2-hydroxy-3,5-di(1,1-dimethylbenzyl) phenyl]-2H-benzotriazole CAS NO. 70321-86-7 PW, FF		448	137.0 ~ 141.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 2.5 Ethanol < 0.1 Toluene 18.1 Xylene 13.1 Ethyl acetate 5.1	337 357 409	5% 10% 50%
SONGSORB® 3260 2-(2'-hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole CAS NO. 3896-11-5 PW		316	138.0 ~ 141.0	Squalane 0.7 n-Hexane 1.5 Acetone 1.5 Ethanol 0.1 Toluene 10.4 Xylene 11.8 Ethyl acetate 3.2	217 232 287	5% 10% 50%
SONGSORB® 3290 2-(2H-benzotriazole-2-yl)-4-(1,1,3,3-tetramethylbutyl) phenol CAS NO. 3147-75-9 PW, FF		323	103.0 ~ 105.0	Squalane 0.3 n-Hexane 6.0 Acetone 11.5 Ethanol < 0.1 Toluene 44.7 Xylene 49.0 Ethyl acetate 21.3	223 243 302	5% 10% 50%
SONGSORB® 3600 Bis[2-hydroxy-5-tert-octyl-3-(benzotriazole-2-yl)phenyl]methane CAS NO. 103597-45-1 PW, FF		659	192.0 ~ 198.0	Squalane < 0.05 n-Hexane < 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene 3.7 Xylene 2.6 Ethyl acetate 0.4	369 393 449	5% 10% 50%
SONGSORB® 5710 2-(2H-Benzotriazol-2-yl)-4-methyl-(5 or 6)-dodecyl phenol CAS NO. 125304-04-3 / 23328-53-2 (KR) LQ		395	—	n-Hexane > 50 Acetone > 50 Ethanol 2.0 Toluene > 50 Xylene > 50 Ethyl acetate > 50	238 254 300	5% 10% 50%

UV Absorbers
(UVAs)

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)		TGA (°C, % mass loss)	
SONGSORB® 7120 2,4-di-tert-butylphenyl-4'-hydroxy-3',5'-di-tert-butyl benzoate CAS NO. 4221-80-1 PW		439	194.0 ~ 197.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 0.8 11.0 0.3 16.4 10.0 13.2	252 268 318	5% 10% 50%
SONGSORB® 2908 Hexadecyl-3,5-di-tert-butyl-4-hydroxybenzoate CAS NO. 67845-93-6 PW		475	55.0 ~ 65.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	0.9 35.0 14.0 0.6 > 50.0 > 50.0 26.0	271 288 349	5% 10% 50%
SONGSORB® 8100 2-hydroxy-4-n-octoxybenzophenone CAS NO. 1843-05-6 PW		326	> 47.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	0.3 18.0 > 50.0 1.0 > 50.0 > 50.0 > 50.0	280 297 344	5% 10% 50%
SONGSORB® 3120 2-ethyl-2'-ethoxy-oxanilide CAS NO. 23949-66-8 PW		312	124.0 ~ 128.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.01 < 0.1 < 5.0 < 0.2 7.0 4.5 5.0	246 262 301	5% 10% 50%
SONGSORB® 1577 2-(4,6-diphenyl-1,3,5-triazin-2-yl)-5-hexyloxyphenol CAS NO. 147315-50-2 PW, FF		425	147.0 ~ 151.0	Squalane n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	< 0.05 < 0.1 0.2 < 0.1 6.3 5.5 0.8	313 329 378	5% 10% 50%
SONGSORB® 1164 2-[4,6-bis (2,4-dimethylphe-nyl)-1,3,5-triazin-2-yl]-5-(octyloxy) phenol CAS NO. 2725-22-6 PW, FF		509	88.0 ~ 93.0	n-Hexane Acetone Ethanol Toluene Xylene Ethyl acetate	0.6 0.2 0.1 29.1 21.8 2.6	349 371 419	5% 10% 50%

Binary Blends

Product Name	SONGNOX® 1680	SONGNOX® 1010	SONGNOX® 1076	SONGNOX® 3114	Physical Forms
SONGNOX® 11B	1	1	0	0	PW, FF
SONGNOX® 21B	2	1	0	0	PW, FF
SONGNOX® 31B	3	1	0	0	PW, FF
SONGNOX® 41B	4	1	0	0	PW, FF
SONGNOX® 117B	1	0	1	0	PW, FF
SONGNOX® 217B	2	0	1	0	PW, FF
SONGNOX® 417B	4	0	1	0	PW, FF
SONGNOX® 147B	1	0	4	0	PW, FF
SONGNOX® 311B	1	0	0	1	PW, FF
SONGNOX® 321B	2	0	0	1	PW, FF

The numbers shown in the tables refer to the ratios of the ingredients in the binary blends.

Liquid Blends

Product Name	SONGNOX® 1135	SONGNOX® 5057	SONGSORB® 5710	SONGSORB® 2920	Physical Forms
SONGNOX® 5721	2	1			LQ
SONGSORB® B5075	1		2	2	LQ

The numbers shown in the tables refer to the ratios of the ingredients in the blends.

One Pack System Blends (OPS)

SONGNOX® OPS (One Pack Systems) are customized additive blends that are available in different physical forms. OPS products increase operational efficiency and can lower overall additivation costs.

SONGXTEND® – Application-Specific Stabilizers

- **SONGXTEND® 2124:**
High heat stabilization in polypropylene-based automotive applications
- **SONGXTEND® 1301:**
Stabilizer for expanded and extruded polystyrene containing polymeric flame retardants
- **SONGXTEND® 2721:**
Top-up, quality enhancing stabilization system for more sustainable PP recycled resins

Standard Packaging

- **Antioxidants, solids:** 20 kg PE bag
(20 kg aluminum coated bags for SONGNOX® 6260, SONGNOX® 6280, SONGNOX® 9228, SONGNOX® 9228T and SONGNOX® PQ)
500 kg big bag
for US and selected products only: 50 kg fiber drum
- **Antioxidants, liquids:** 200 kg steel drum
900 kg IBC
20 MT ISO tank
- **Thioesters:** 20 kg PE bag
500 kg big bag
- **Hindered amine light stabilizers:** 20 kg PE bag
500 kg big bag
- **UV absorbers, solids:** 20 kg bag in a carton
25 kg bag in a carton
- **UV absorbers, liquids:** 20 kg HDPE drum
200 kg Steel drum

Key to Abbreviations of Physical Forms

- **PW:** Powder
- **FF:** Free Flow
- **DF:** Dust Free Flow
- **FG:** Fine Grind
- **SB:** Semi-Beads
- **DW:** Dispersion
- **CP:** Crystalline Powder
- **SL:** Solid
- **LQ:** Liquid or Molten
- **GR:** Granules

Transport and Storage

As a general guideline, we recommend storing the products mentioned in this brochure in their original sealed containers in a cold and dry place. For more detailed information on a specific product, please refer to the corresponding **Technical Data Sheet**.



By law, a number of chemical products must be labeled in respect of transport, storage and handling. Thus corresponding care is a prerequisite for their appropriate handling. Furthermore, local legal regulations may apply.

Detailed information is given in the respective **Safety Data Sheets**.

About SONGWON

A leader in the development, production and supply of specialty chemicals, SONGWON's products touch your life every day, everywhere. Since 1965, we've been driving innovation, partnering for progress and paving the way for a better more sustainable tomorrow with 360° customized solutions.

Headquartered in South Korea, SONGWON is one of the largest manufacturer of polymer stabilizers worldwide. With Group companies and world-class manufacturing facilities across the globe, we are dedicated to providing customers in over 60 countries with high-performance products that meet their individual needs and the best levels of service.

For further information, please go to:
www.songwon.com

SONGWON
INDUSTRIAL
GROUP



For further information, please contact:

techservice@songwon.com

SONGWON provides customers with warranties and representations as to the chemical or technical specifications, compositions and/or the suitability for use for any particular purpose exclusively in individual written agreements.

The facts and figures contained herein have been carefully compiled to the best of SONGWON's knowledge but are essentially intended for informational purposes only.

SONGWON Industrial Group does not accept any liability whatsoever for any information, reference or advice provided in this document or any similar SONGWON publication.

Version 10, February 2026



It's all about **the chemistry[®]**

www.songwon.com