

Polymer Stabilizers
Antioxidants and
Light Stabilizers

Polymer stabilizers protect plastics during manufacture and use

Thanks to light weight, cost effectiveness, flexibility and ease of processing, plastics are being used on an increasing scale in a wide and ever-growing variety of industries and applications. To prevent degradation when exposed to heat, cold and light, plastics require stabilization. Specially designed stabilizers protect the polymer during processing and ensure that plastic end products retain their physical properties during use, prolonging their life.

SONGWON offers a comprehensive range of processing, heat and light stabilizers in a variety of blends and physical forms that facilitate handling and application.

It's all about **the chemistry™**



Product range selection guide

Phenolic Antioxidants

	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 1010															
SONGNOX® 1076															
SONGNOX® 1135															
SONGNOX® 2450															
SONGNOX® 3114															
SONGNOX® 1035															
SONGNOX® 1098															
SONGNOX® 4425															
SONGNOX® 1330															
SONGNOX® 5650															
SONGNOX® 1024															

Aminic Antioxidants

	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 5057															

Phosphite Antioxidants

	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® 1680															
SONGNOX® 6260															
SONGNOX® 6280															
SONGNOX® PQ															

Thioester Antioxidants

	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGNOX® DSTDP															
SONGNOX® DLTDP															
SONGNOX® DMTDP															
SONGNOX® DTDTP															

 Recommended

 Suitable







Hindered Amine Light Stabilizers (HALS)






	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SABO®STAB UV 40															
SABO®STAB UV 62															
SABO®STAB UV 65															
SABO®STAB UV 70															
SABO®STAB UV 91															
SABO®STAB UV 91 50PP															
SABO®STAB UV 94															
SABO®STAB UV 119															
SABO®STAB UV 216															
SABO®STAB UV 228 50PP															
SABO®STAB UV 229 50PP															

UV Absorbers (UVAs)


	ABS	PC/ABS	PC	PU Fibers	Polyamides	Polyesters	Polyethylene	Polypropylene	Polystyrene	Polyurethane	PVC	Elastomers	Acrylics	Polyacetal	TPU
SONGSORB® 1000															
SONGSORB® 2340															
SONGSORB® 3260															
SONGSORB® 3270															
SONGSORB® 3280															
SONGSORB® 3290															
SONGSORB® 3600															
SONGSORB® 9280															
SONGSORB® 7120															
SONGSORB® 2908															
SONGSORB® 8100															
SABO®STAB UV 312															
SONGSORB® 1577															

Phenolic Antioxidants





		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SONGNOX® 1010 Tetrakis[methylene-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate] methane CAS NO. 6683-19-8 PW, FF, DF		1178	110.0 ~ 125.0	Squalane < 0.05 n-Hexane < 0.1 Acetone < 50.0 Ethanol < 0.1 Toluene 48.0 Xylene 24.2 Ethyl acetate > 50.0	353 5% 370 10% 425 50%
SONGNOX® 1076 Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate CAS NO. 2082-79-3 PW, CP, SB, LQ		531	50.0 ~ 55.0	Squalane 0.5 n-Hexane > 50.0 Acetone > 50.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	330 5% 347 10% 387 50%
SONGNOX® 1135 Benzenepropanoic acid, 3,5-bis(1,1-dimethylethyl)-4-hydroxy-, C7-9-branched alkyl esters CAS NO. 125643-61-0 LQ		390	—	Squalane > 50.0 n-Hexane > 50.0 Acetone > 50.0 Ethanol > 50.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	257 5% 278 10% 328 50%
SONGNOX® 2450 Triethylene glycol-bis-3-(3-tert-butyl-4-hydroxy-5-methylphenyl) propionate CAS NO. 36443-68-2 PW, FF, DW		587	76.0 ~ 80.0	Squalane < 0.05 n-Hexane < 0.1 Acetone > 50.0 Ethanol 9.0 Toluene 10.0 Xylene 0.5 Ethyl acetate > 50.0	326 5% 345 10% 396 50%
SONGNOX® 3114 Tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate CAS NO. 27676-62-6 PW, FF		784	218.0 ~ 223.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 45.0 Ethanol < 0.1 Toluene 22.0 Xylene 21.0 Ethyl acetate 45.0	330 5% 344 10% 374 50%
SONGNOX® 1035 Thiodiethylenebis[3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate] CAS NO. 41484-35-9 PW, FF		643	> 65.0	Squalane < 0.05 n-Hexane 0.8 Acetone > 50.0 Ethanol 1.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	322 5% 339 10% 375 50%

SONGNOX® 1098 N,N'-hexamethylenebis(3,5-di-tert-butyl-4-hydroxyhydrocinnamamide) CAS NO. 23128-74-7 PW, FF, GR, DW		637	156.0 ~ 162.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 2.5 Ethanol 5.5 Toluene < 0.1 Xylene < 0.1 Ethyl acetate 0.7	336 5% 350 10% 418 50%
SONGNOX® 4425 4,4'-butylidenebis(6-tert-butyl-3-methylphenol) CAS NO. 85-60-9 PW		383	208.0 ~ 214.0	Squalane < 0.05 n-Hexane < 0.1 Acetone > 50.0 Ethanol 29.0 Toluene 1.0 Xylene < 0.1 Ethyl acetate > 50.0	249 5% 265 10% 316 50%
SONGNOX® 1330 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene CAS NO. 1709-70-2 PW, FF		775	241.0 ~ 247.0	Squalane < 0.05 n-Hexane 0.9 Acetone 22.0 Ethanol < 0.1 Toluene 30.0 Xylene 22.0 Ethyl acetate 36.0	368 5% 391 10% 446 50%
SONGNOX® 5650 2,6-di-tert-butyl-4-(4,6-bis(octylthio)-1,3,5-triazin-2-ylamino) phenol CAS NO. 991-84-4 PW, GR		589	94 ~ 96	Squalane < 0.05 n-Hexane 6.50 Acetone > 50.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	348.35 5% 361.67 10% 401.26 50%
SONGNOX® 1024 1,2-bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl) hydrazine CAS NO. 32687-78-8 PW, FF, FG		553	221.0 ~ 232.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 5.0 Ethanol 1.0 Toluene < 0.1 Xylene < 0.1 Ethyl acetate 0.6	307 5% 319 10% 359 50%





Aminic Antioxidants

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SONGNOX® 5057 Mixture of butylated & octylated diphenylamine CAS NO. 68411-46-1 LQ		Mixture of butyl, octyl diphenylamine	—	Squalane > 50 n-Hexane > 50 Acetone > 50 Ethanol > 50 Toluene > 50 Xylene > 50 Ethyl acetate > 50	235 5% 255 10% 320 50%






Phosphite Antioxidants




		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SONGNOX® 1680 Tris(2,4-di-tert-butylphenyl) phosphite CAS NO. 31570-04-4 PW, FF		647	181.0 ~ 187.0	Squalane < 0.05 n-Hexane 10.0 Acetone 1.3 Ethanol < 0.1 Toluene 25.0 Xylene 24.0 Ethyl acetate 5.0	286 5% 305 10% 362 50%
SONGNOX® 6260 Bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite CAS NO. 26741-53-7 PW, FF		605	170.0 ~ 180.0	Squalane < 0.05 n-Hexane 2.0 Acetone 3.0 Ethanol < 0.1 Toluene 26.0 Xylene 17.0 Ethyl acetate 0.7	306 5% 329 10% 382 50%
SONGNOX® 6280 SONGNOX® 6260: Mg, Al talcite = 93 : 7 CAS NO. 26741-53-7, 11097-59-9 PW, FF	 $Mg_{1-x}Al_x(OH)_2 \cdot (CO_2)_x \cdot nH_2O$	—	—	—	—
SONGNOX® PQ Phosphorous trichloride, reaction products with 1,1'-biphenyl and 2,4-bis(1,1-dimethylethyl) phenol CAS NO. 119345-01-6 PW, SB		1035	75.0 ~ 100.0	Squalane 0.1 n-Hexane > 50.0 Acetone 9.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	296 5% 325 10% 423 50%

Thioester Antioxidants

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SONGNOX® DSTDP Distearyl thiodipropionate CAS NO. 693-36-7 PW, SB		683	63.5 ~ 68.5	Squalane 0.1 n-Hexane 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene 4.6 Xylene 4.1 Ethyl acetate < 0.1	324 5% 348 10% 389 50%
SONGNOX® DLTDP Dilauryl thiodipropionate CAS NO. 123-28-4 PW, SB, LQ		515	38.0 ~ 41.0	Squalane 2.6 n-Hexane > 50.0 Acetone > 50.0 Ethanol 0.3 Toluene > 50.0 Xylene 46.0 Ethyl acetate 29.0	284 5% 313 10% 361 50%
SONGNOX® DMTDP Dimyristyl thiodipropionate CAS NO. 16545-54-3 PW, SB		571	49.0 ~ 54.0	Squalane < 0.05 n-Hexane 8.0 Acetone 2.0 Ethanol < 0.1 Toluene 41.0 Xylene 33.0 Ethyl acetate 4.1	296 5% 316 10% 367 50%
SONGNOX® DTDTP Ditridecyl thiodipropionate CAS NO. 10595-72-9 LQ		543	—	Squalane > 50.0 n-Hexane > 50.0 Acetone > 50.0 Ethanol 5.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	300 5% 331 10% 374 50%

Hindered Amine Light Stabilizers (HALS)






		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SABO®STAB UV 40 1,6-hexanediamine, N,N'-bis (2,2,6,6-tetramethyl-4-piperidyl)-, polymer with 2,4,6-trichloro-1,3,5-triazine, reaction products with N-butyl-1-butanamine and N-butyl-2,2,6,6-tetramethyl-4-piperidinamine CAS NO. 192268-64-7 MB		2600 ~ 3400	120.0 ~ 150.0	n-Hexane > 50.0 Acetone > 50.0 Water < 0.0001	390 5% 420 10%
SABO®STAB UV 62 Butanedioic acid, 1,4-dimethyl ester, polymer with 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine-ethanol CAS NO. 65447-77-0 PW, BD		3100 ~ 4000	(Softening) 50.0 ~ 70.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 39.0 Ethanol < 0.1 Toluene 7.1 Xylene 35.0 Ethyl acetate 21.0	334 5% 342 10% 366 50%
SABO®STAB UV 65 Bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate methyl 1,2,2,6,6-pentamethyl-4-piperidyl sebacate CAS NO. 41556-26-7 LQ		509	—	Squalane > 50.0 n-Hexane > 50.0 Acetone > 50.0 Ethanol > 50.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	265 5% 293 10% 347 50%
SABO®STAB UV 70 Bis(2,2,6,6-tetramethyl-4-piperidyl) sebacate CAS NO. 52829-07-9 GR		481	81.0 ~ 85.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 35.0 Ethanol > 50.0 Toluene > 50.0 Xylene 49.0 Ethyl acetate 38.1	249 5% 264 10% 301 50%
SABO®STAB UV 78 Mixture of SABO®STAB UV 62 and SABO®STAB UV 94 BD	SABO®STAB UV 62 : SABO®STAB UV 94 = 1 : 1	—	—	—	—
SABO®STAB UV 91 Fatty acids, C12-21 and C18-unsaturated, 2,2,6,6-tetramethyl-4-piperidyl esters CAS NO. 167078-06-0 SL	 n=10-19 mainly 14-16	—	> 28.0	Squalane 1.0 n-Hexane 0.5 Acetone 1.5 Ethanol 8.5 Toluene 29.0 Xylene 23.2 Ethyl acetate 2.5	227 5% 241 10% 278 50%

SABO®STAB UV 91 50PP 2,2,6,6-tetramethylpiperidine-4-yl-hexadecanoate and 2,2,6,6-tetramethylpiperidine-4-yl-octadecanoate CAS NO. 86403-32-9 (EU) 167078-06-0 (rest of the world) GR		—	—	n-Hexane 49.0 Acetone 2.2 Ethanol 37.0 Toluene 25.0 Ethyl acetate 4.0 Water < 0.01	248 5% 261 10%
SABO®STAB UV 94 1,6-hexanediamine, N,N'-bis (2,2,6,6-tetramethyl-4-piperidyl)-, polymer with 2,4,6-trichloro-1,3,5-triazine, reaction products with 2,4,4-trimethyl-2-pentanamine CAS NO. 71878-19-8 BD		2000 ~3100	(Softening) 100.0 ~ 135.0	Squalane < 0.05 n-Hexane 6.0 Acetone > 50.0 Ethanol < 0.1 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	403 5% 426 10% 472 50%
SABO®STAB UV 119 1,3,5-triazine-2,4,6-triamine, N2,N2"-1,2-ethanediylbis [N2-[3-[[4,6-bis[butyl (1,2,2,6,6-pentamethyl-4-piperidyl)amino]-1,3,5-triazin-2-yl]amino]propyl]-N',N"-dibutyl-N',N"-bis (1,2,2,6,6-pentamethyl-4-piperidyl)- CAS NO. 106990-43-6 PS		2286	115.0 ~ 150.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 0.2 Ethanol < 0.1 Toluene 25.0 Xylene 24.0 Ethyl acetate 0.9	362 5% 381 10% 457 50%
SABO®STAB UV 216	Superior light- and long-term thermal stabilizer for greenhouse films applications in presence of pesticides				
SABO®STAB UV 228 50PP	For automotive interior use (e.g., dashboards or door panels); for building and construction applications (e.g., TPO roofing membranes)				
SABO®STAB UV 229 50PP	For automotive interior use (e.g., dashboards or door panels); for building and construction applications (e.g., TPO roofing membranes)				



UV Absorbers (UVAs)

		Molecular Weight	Melting Range (°C)	Solubility (g/100 g solvent at 25°C)	TGA (°C, % mass loss)
SONGSORB® 1000 2-(2'-hydroxy-5'-methylphenyl) benzotriazole CAS NO. 2440-22-4 PW		225	128.0 ~ 132.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 3.0 Ethanol < 0.1 Toluene 7.1 Xylene 6.1 Ethyl acetate 5.1	225 5% 242 10% 289 50%
SONGSORB® 2340 2-[2-hydroxy-3,5-di(1,1-dimethylbenzyl) phenyl]-2H-benzotriazole CAS NO. 70321-86-7 PW, FF		448	137.0 ~ 141.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 2.5 Ethanol < 0.1 Toluene 18.1 Xylene 13.1 Ethyl acetate 5.1	337 5% 357 10% 409 50%
SONGSORB® 3260 2-(2'-hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole CAS NO. 3896-11-5 PW		316	138.0 ~ 141.0	Squalane 0.7 n-Hexane 1.5 Acetone 1.5 Ethanol 0.1 Toluene 10.4 Xylene 11.8 Ethyl acetate 3.2	217 5% 232 10% 287 50%
SONGSORB® 3270 2-(2'-hydroxy-3',5'-di-tert-butylphenyl)-5-chlorobenzotriazole CAS NO. 3864-99-1 PW		358	154.0 ~ 157.0	Squalane 0.9 n-Hexane 4.0 Acetone 2.0 Ethanol 0.1 Toluene 23.3 Xylene 20.6 Ethyl acetate 6.2	223 5% 239 10% 290 50%
SONGSORB® 3280 2-(2'-hydroxy-3',5'-di-tert-amylphenyl)benzotriazole CAS NO. 25973-55-1 PW		352	80.0 ~ 88.0	Squalane 3.3 n-Hexane 20.0 Acetone 8.0 Ethanol 0.3 Toluene < 50.0 Xylene < 50.0 Ethyl acetate 30.0	222 5% 236 10% 283 50%
SONGSORB® 3290 2-(2H-benzotriazole-2-yl)-4-(1,1,3,3-tetramethylbutyl) phenol CAS NO. 3147-75-9 PW, FF		323	103.0 ~ 105.0	Squalane 0.3 n-Hexane 6.0 Acetone 11.5 Ethanol < 0.1 Toluene 44.7 Xylene 49.0 Ethyl acetate 21.3	223 5% 243 10% 302 50%
SONGSORB® 3600 Bis[2-hydroxy-5-tert-octyl-3-(benzotriazole-2-yl)phenyl] methane CAS NO. 103597-45-1 PW, FF		659	192.0 ~ 198.0	Squalane < 0.05 n-Hexane < 0.1 Acetone < 0.1 Ethanol < 0.1 Toluene 3.7 Xylene 2.6 Ethyl acetate 0.4	369 5% 393 10% 449 50%
SONGSORB® 9280 2-Hydroxy-3-(1,1-dimethylbenzyl)-5-(1,1,3,3-tetramethylbutyl)phenyl]-2H-benzotriazole CAS No. 73936-91-1 PW		442	108.0 ~ 113.0	Squalane 0.15 n-Hexane 10.10 Acetone 10.20 Ethanol 0.15 Toluene > 50 Xylene > 50 Ethyl acetate 28.6	254 5% 270 10% 314 50%

SONGSORB® 7120 2,4-di-tert-butylphenyl-4'-hydroxy-3',5'-di-tert-butylbenzoate CAS NO. 4221-80-1 PW		439	194.0 ~ 197.0	Squalane < 0.05 n-Hexane 0.8 Acetone 11.0 Ethanol 0.3 Toluene 16.4 Xylene 10.0 Ethyl acetate 13.2	252 268 318	5% 10% 50%
SONGSORB® 2908 Hexadecyl-3,5-di-tert-butyl-4-hydroxybenzoate CAS NO. 67845-93-6 PW		475	55.0 ~ 65.0	Squalane 0.9 n-Hexane 35.0 Acetone 14.0 Ethanol 0.6 Toluene > 50.0 Xylene > 50.0 Ethyl acetate 26.0	271 288 349	5% 10% 50%
SONGSORB® 8100 2-hydroxy-4-n-octoxybenzophenone CAS NO. 1843-05-6 PW		326	> 47.0	Squalane 0.3 n-Hexane 18.0 Acetone > 50.0 Ethanol 1.0 Toluene > 50.0 Xylene > 50.0 Ethyl acetate > 50.0	280 297 344	5% 10% 50%
SABO®STAB UV 312 2-ethyl-2'-ethoxy-oxanilide CAS NO. 23949-66-8 PW		312	124.0 ~ 128.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 4.0 Ethanol < 0.1 Toluene 7.3 Xylene 5.2 Ethyl acetate 5.0	266 286 333	5% 10% 50%
SONGSORB® 1577 2-(4,6-diphenyl-1,3,5-triazin-2-yl)-5-hexyloxyphenol CAS NO. 147315-50-2 PW		425	147.0 ~ 151.0	Squalane < 0.05 n-Hexane < 0.1 Acetone 0.2 Ethanol < 0.1 Toluene 6.3 Xylene 5.5 Ethyl acetate 0.8	313 329 378	5% 10% 50%

All SABO®STAB products are exclusively produced by SABO S.p.A.



Binary Blends

Product Name	SONGNOX® 1680	SONGNOX® 1010	SONGNOX® 1076	SONGNOX® 3114	Physical Forms
SONGNOX® 11B	1	1	0	0	PW, FF
SONGNOX® 21B	2	1	0	0	PW, FF
SONGNOX® 31B	3	1	0	0	PW, FF
SONGNOX® 35B	3	5	0	0	PW, FF
SONGNOX® 41B	4	1	0	0	PW, FF
SONGNOX® 43B	4	3	0	0	PW, FF
SONGNOX® 56B	5	6	0	0	PW, FF
SONGNOX® 117B	1	0	1	0	PW, FF
SONGNOX® 217B	2	0	1	0	PW, FF
SONGNOX® 317B	3	0	1	0	PW, FF
SONGNOX® 417B	4	0	1	0	PW, FF
SONGNOX® 147B	1	0	4	0	PW, FF
SONGNOX® 311B	1	0	0	1	PW, FF
SONGNOX® 321B	2	0	0	1	PW, FF
SONGNOX® 1711B	0	1	1	0	PW, FF

The numbers shown in the tables refer to the ratios of the ingredients in the binary blends.

Product Name	SONGNOX® 1135	SONGNOX® 5057	Physical Forms
SONGNOX® 5721	2	1	LQ

The numbers shown in the tables refer to the ratios of the ingredients in the binary blends.

One Pack System Blends (OPS)

SONGNOX® OPS (One Pack Systems) are customized additive blends that are available in different physical forms. OPS products increase operational efficiency and can lower overall additivition costs.

SONGXTEND® – Stabilizer Solutions

- **SONGWON solutions for polypropylene film grades**
SONGXTEND® 1102
- **SONGWON solutions for the stabilization of polypropylene fiber and thin walled injection molded grades**
SONGXTEND® 1140, SONGXTEND® 1141
- **SONGWON solutions for low VOC automotive applications**
SONGXTEND® 1103, SONGXTEND® 2123, SONGXTEND® 2124

Standard Packaging

- **Antioxidants, Solids:** 20 kg PE Bag
(20 kg aluminum coated bags for SONGNOX® 6260, 6280 and 621B)
500 kg Big Bag
for US and selected products only: 50 kg Fiber Drum
- **Antioxidants, Liquids:** 200 kg Steel Drum
900 kg IBC
20 MT ISO Tank
- **Thioesters:** 20 kg PE Bag (SONGNOX® 4120: 25 kg Carton Box)
- **Hindered Amine Light Stabilizers:** 25 kg PE Bag
(for SABO®STAB 119: 15 kg PE Bag; for SABO®STAB 312: 20 kg PE Bag)
- **UV Absorbers:** 20 kg Carton Box
25 kg Carton Box

Standard pallet size is CP1.

Key to Abbreviations of Physical Forms

- | | | | |
|------------------------|-------------------------------|---------------------------------|-----------------------------|
| • PW: Powder | • DW: Dispersion | • BD: Beads | • GR: Granule |
| • SB: Semi Bead | • MB: Micro Beads | • DF: Dust Free Flow | • FG: Fine Grind |
| • SL: Solid | • FC: Fusion Crystal | • CP: Crystalline Powder | • VL: Viscous Liquid |
| • FF: Free Flow | • LQ: Liquid or Molten | • PS: Pastilles | |



Transport and Storage

As a general guideline, we recommend storing the products mentioned in this brochure in their original sealed containers in a cold and dry place. For more detailed information on a specific product, please refer to the corresponding **Technical Data Sheet**.

By law, a number of chemical products must be labeled in respect of transport, storage and handling. Thus corresponding care is a prerequisite for their appropriate handling. Furthermore, local legal regulations may apply.

Detailed information is given in the respective **Safety Data Sheets**.

About SONGWON Industrial Group

SONGWON, which was founded in 1965 and is headquartered in Ulsan, South Korea, is a leader in the development, production and supply of specialty chemicals.

The second largest manufacturer of polymer stabilizers worldwide, SONGWON Industrial Group operates companies all over the world, offering the combined benefits of a global framework and readily accessible local organizations.

Dedicated experts work closely together with customers to develop tailor-made solutions that meet individual requirements.

For further information, please go to:

www.songwon.com





For further information, please go to:

www.songwon.com

techservice@songwon.com

SONGWON provides customers with warranties and representations as to the chemical or technical specifications, compositions and/or the suitability for use for any particular purpose exclusively in individual written agreements.

The facts and figures contained herein have been carefully compiled to the best of SONGWON's knowledge but are essentially intended for informational purposes only.

SONGWON Industrial Group does not accept any liability whatsoever for any information, reference or advice provided in this document or any similar SONGWON publication.

Version 7, November 2019